

Data Sheet: CW510L

FREE MACHINING

ALLOY: CW510L

Lead free alloy.

Included in the 4MS Positive List.

ALLOY DESIGNATION

UNIEN: CW510L - CuZn42

ASTM: C28500

CHEMICAL COMPOSITION UNI EN 12164 ED.2016

Cu	Pb	Sn	Fe	Ni*	Al	Zn	Other elements
Min 57,0% max 59,0%	≤0.1 %	≤0.3 %	≤0.3 %	≤0.2 %	≤0.05 %	difference	≤0.2 %

Restrictions according to 4MS. Each unnamed element must be less than 0.02%.

Restriction group of the surface in contact with drinking water according to the «common composition list»: C and D.

HEAT TREATMENTS

STRESS RELIEVING It specifically allows redistribution of tension induced by machining or cold plastic deformation, reducing the risk of stress corrosion cracking.

TREATMENT: heating of parts at 200°C to 250°C for 2 hours and cooling within the furnace. Validation of stress relief treatment can be performed with the ISO 6957 test.

ANNEALING

Recrystallization of the alloy reduces hardness and increases ductility. The treatment temperature ranges from 450°C to 550°C for a period of time relative to the intended result. The high temperature can cause variations in the surface appearance and tolerances of the finished part.



Lead free alloy.

Included in the 4MS Positive List.

TECHNOLOGICAL PROPERTIES

Structure	Density	Electrical conductivity	Coeff. of thermal expansion	Thermal conductivity*	Specific heat	Elasticity module	Melting point
α + β	8.4 kg/ <i>cm</i> ²	27% IACS	21.2 10 ⁻⁶ /K	112 W/(m K)	381 J/(kg K)	85 KN/mm²	870-890 °C

low 0 0 0 0 0 0 excellent

Machinability: ● ● ● ○ ○ ○ ○ ○ Weldability: ● ● ● ● ○ ○ ○ ○ Hot forming: ● ● ● ● ○ ○ ○

Cold Forming: ● ● ○ ○ ○ ○ ○ ○ ○ Corrosion resistance**: ○ ○ ○ ○ ○ ○

MECHANICAL PROPERTIES UNI EN 12164 ED.2016

Condition of	Diameter in mm		Hardness HB*		Rm	Rp0,2.N/mm²		Elongation %
material	from	to (included)	min.	max	min.	min.	max	min.
М	ALL		AS MANU		JFACTURED			
R360	6 (5)	80 (60)	-	-	360	-	320	20
H090	6 (5)	80 (60)	90	125	-	-	-	-
R430	2	40 (35)	-	-	430	220	-	10
H110	2	40 (35)	110	160	-	-	-	-
R500	2	14 (10)	-	-	500	350	-	5
H135	2	14 (10)	135	-	-	-	-	-

^{*}Hardness values are determined in the mid-range.



^{*}at room temperature.

**compatibility with chemical substances should be carefully checked.

Values in brackets refer to the hexagonal section bar.

The standard condition produced by Metallurgica San Marco is M.

Other conditions must be requested at the time of order after a feasibility inquiry.

Lead free alloy.

Included in the 4MS Positive List.

DIMENSIONS, TOLERANCES, AND STRAIGHTNESS UNI EN 12164 ED.2016

	ROL	JND section	bar	HEXAGONA	L and SQUARE	section bar	
Nominal dia	ameter (mm)		TOLERANCES		Nominal key (mm)		Tolerance (mm)
from	to included	Class A	Class B	Class C	from	to included	Tolerance (IIIII)
6	10	0 – 0.06	0 – 0.036	0 – 0.025	6	10	0 – 0.09
10	18	0 – 0.07	0 – 0.043		10	18	0 – 0.11
18	30	0 – 0.08	0 – 0.052		18	30	0 – 0.13
30	50	0 – 0.16			30	50	0 – 0.16
50	80	0 – 0.19			50	60	0 – 0.19

The standard tolerance for the round bar is Class A. Different tolerances must be defined when ordering. Supplies of semi-finished products from Ø63 to Ø80 mm with Class A tolerances are possible.

	neter m)	Lenght of bar (mm)	Tolerance (mm)	
2	30	3000 o 4000	+/- 50	
30	50	3000 o 4000	+/- 100	
50	80	3000	+/- 100	


Dian	neter	Deviation from straightness in mm				
(m	m)	Every 400 mm	Every m of length L≥1			
	Round section bar					
10	50	0.4	1,0 x L			
	Hexagonal and square section bar					
10	50	0.6	1.5 x L			

Lead free alloy.

Included in the 4MS Positive List.

FINISHING AND PACKAGING

Diameter or Key (mm)			r or Key m)	Tip Length L (mm)		
5	10	0.2	1.5	2	7	
10	20	0.2	2	3	10	
20	30	0.2	3	4	12	



Unless otherwise specified by the buyer, the shape of the ends of products larger than 30 mm is at the discretion of the supplier.

Ends of round bars	finishing with chamfer and point up to and including Ø55 mm.					
Enus of round pars	finishing with saw cut greater than Ø55 mm.					
Ends of hexagonal bars	Finishing with chamfer and cut. Other finishing available on request.					
Bar surface	Pickled.					
Packaging	1000 kg bundle - 3/5 metal straps. Different bundle packaging and quantities are possible on specific request.					
Identification	Adhesive label on strap or bar ends.					
Stress relieving	Polygonal bar undergoes the heat treatment of stress relief.					

TECHNICAL NOTES

Lead-free alloy, which can be used in the U.S. market and in areas where extremely low lead content is required. This alloy is included in the Positive List of metallic materials suitable for use in contact with potable water.

